

# UCRETE® UD200

Heavy duty polyurethane concrete flooring system

## DESCRIPTION

**Ucrete UD200** is a single layer, seamless, solvent-free, polyurethane flooring system. It has a textured matt finish possessing a wide spectrum of chemical resistance; withstands abrasive wear; has high impact resistance and withstands direct steam impact.

## RECOMMENDED FOR

**Ucrete UD200** is recommended for conditions requiring the maximum of chemical resistance, health and safety and where thermal situations arise, from cool rooms to hot environments.

Specific applications include:

- meat, fish and poultry processing
- food and beverage production
- dairies, cheese and milk products
- cold rooms, chillers and freezers
- pharmaceutical production
- chemical plants

## FEATURES AND BENEFITS

<b>Expert application</b>	Installed only by trained and approved specialist contractors.
<b>Fast application/rapid access</b>	Can be applied to 6-day-old concrete or 2 day old polymer screeds. Short curing time and 8 hour access to foot traffic; 24 hours for vehicles.
<b>Hygienic/safe</b>	Slip resistant, non-tainting, non-dusting, monolithic (minimum joints), easy to maintain, microbiologically inert.
<b>Durable/long life</b>	Wide chemical resistance, wear and impact resistant, resists temperatures from -40°C to 120°C at 9 mm thickness; 25 years of international use.
<b>Prepacked</b>	Preweighed/ prepacked for immediate use; batch to-batch colour matched for consistency.

## TYPICAL PERFORMANCE DATA

(After 28 days @ 20°C)

Compressive Strength (BS6319:Part 2)	: 58 MPa
Flexural Strength (ISO178)	: 14 MPa
Dynamic E-Modulus (ASTM C597-83)	: 19.5 GPa
Tensile Strength (ISO R527)	: 6 MPa
Concrete Adhesion (BS6319:Part2)	: concrete fails
Abrasion Resistance (Taber H22)	: 1390mg
Coeff. Thermal Expansion (ASTM C531)	: $2.4 \times 10^{-5} \text{ } ^\circ\text{C}^{-1}$
Thermal Conductivity (BS874)	: 1.1W/m°C
Surface Resistivity (BS2050)	: $3 \times 10^{-4} \text{ ohms}$
Density (BS6319:Part 5)	: 2090 kg/m <sup>3</sup>
Water Adsorption (CP.BM 2/67/2)	: 0 mL
Surface Spread of Flame (BS476:Part 7)	: <b>Class 2</b>

## PROPERTIES

Colours	:	Yellow ~	RAL 1004
		Cream ~	RAL 1014
		Orange ~	RAL 2010
		Red ~	RAL 3001
		Green ~	RAL 6010
		Grey ~	RAL 7037
Thickness	:	4 to 9 mm.	
Service temperatures:			
at 9 mm			
at 4 mm	:	120°C maximum & - 40°C	
	:	60°C maximum & - 15°C	

## APPLICATION

### Surface Preparation

Concrete shall be clean, structurally sound and free from foreign materials, contaminants, oily products and other debris. Concrete surfaces shall be 'visibly dry' with no standing water. The minimum tensile (pull-off) strength shall be 1.5N/mm<sup>2</sup> and concrete shall have cured for at least 5 days. Concrete substrates shall incorporate a continuous waterproofing membrane.

Concrete design shall allow provisions for movement joints, as required. In addition, provision shall be made for induced joints to allow any shrinkage of the concrete to occur along defined planes.

All laitance shall be removed. All imperfections such as holes and cracks shall be repaired and levelled with the mean level of the surface. For repairing surface unevenness, **EMACO**® concrete repair systems shall be used.

The whole surface shall be enclosed or impact shot blasted, surface planed, ground or high-pressure water jetted. All high spots shall be removed. Surfaces shall be rendered 'visibly dry' by heat or mechanical means.

Remove all loose material and dust by vacuum or mechanical means.

### Priming

**Ucrete UD200** shall be applied to a cured scratch coat of **Ucrete MF** of 1 mm nominal thickness.

### Placing

**Ucrete UD200** shall be mixed and applied only by specialist flooring contractors who have been trained in the correct application procedures.

## CURING

At 30°C, foot traffic access in 8 hours; vehicular traffic in 16 hours. At 20°C, foot traffic access in 12 hours; vehicular traffic in 24 hours.



The Chemical Company

# UCRETE<sup>®</sup> UD200

## CLEANING

Regular cleaning, dry or wet mechanical scrubbing or hot flushing with detergents or detergent/ sterilant product will enhance the floor's appearance and reduce soiling tendencies. Direct steam cleaning is suitable for floors applied at more than 8mm thickness.

## ESTIMATING DATA

2.45 to 2.50 kg/m<sup>2</sup>/mm thickness

## PACKAGING

Ucrete UD200 is supplied as complete units for immediate use, consisting of:

Ucrete UD200 Part 1 for AP*	:	2.83 kg
Ucrete UD200 Part 2 for AP*	:	2.86 kg
Ucrete UD200 Part 3 for AP*	:	24 kg

\* Asia Pacific Region

## SHELF LIFE

Ucrete UD 200 can be kept for 12 months from date of manufacture if stored above ground level in original unopened packing under cover, avoiding direct sunlight impingement and at 30°C or less.

## PRECAUTIONS

Material Safety Data Sheets (MSDS) for each component of Ucrete UD200 are available. Gloves and eye protection shall be worn during mixing and application.

For detailed Health, Safety and Environmental recommendation, please consult and follow instructions on the product Material Safety Data Sheet.

All BASF Construction Chemicals Australia & New Zealand data sheets are updated on a regular basis, it is the user's responsibility to obtain the most recent issue **AUcUD200/6/0906**

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF Construction Chemicals** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF Construction Chemicals** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF Construction Chemicals**, are responsible for carrying out procedures appropriate to a specific application.

<b>BASF Construction Chemicals Australia Pty Ltd</b>	Newcastle (02) 4961 3819	Adelaide (08) 8139 7500
Incorporated in NSW A.B.N. 46 000 450 288	Canberra (02) 6280 6010	Perth (08) 9366 2600
Head Office: 11 Stanton Road Seven Hills, NSW 2147	Brisbane (07) 3633 9900	Darwin (08) 8984 3269
Ph. (02) 8811 4200	Townsville (07) 4774 7344	Kalgoorlie 0417 772 355
	Melbourne (03) 9567 7300	

**BASF Construction Chemicals New Zealand Ltd** Head Office: 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233  
BASF WEB SITES [www.basf-cc.com.au](http://www.basf-cc.com.au) [www.basf-cc.co.nz](http://www.basf-cc.co.nz) [www.basf-ugc.com](http://www.basf-ugc.com)