

UCRETE[®] MF

Medium duty polyurethane concrete flooring system

DESCRIPTION

Ucrete MF is a single layer, seamless, solvent-free, polyurethane flooring system with a smooth matt surface finish. It has high impact resistance and withstands abrasive wear and a wide spectrum of chemicals.

RECOMMENDED FOR

Ucrete MF is recommended for conditions requiring the maximum chemical resistance and where a smooth, even and easy to clean surface is required.

Specific applications include:

- textile and film plants
- food and beverage production
- warehousing and storage
- confectionery production
- electronic component manufacture & assembly
- pharmaceutical production
- chemical plants

FEATURES AND BENEFITS

Expert application Installed only by trained and approved specialist contractors.

Fast application / rapid access Can be applied to 6-day-old concrete/2-day-old polymer screeds. Short curing time with 8 hour access to foot traffic; 24 hours for vehicles.

Hygienic/safe Non-tainting, non-dusting, monolithic (minimum joints); easy to maintain; microbiologically inert.

Durable/long life Wide chemical resistance; wear and impact resistant; resists temperatures up to 60°C at 6 mm thickness; 25 years of international use.

Prepacked Preweighed / prepacked for immediate use; batch-to-batch colour matched for consistency.

TYPICAL PERFORMANCE DATA

(Test data 28 days @ 20°C)

Compressive Strength (BS6319:Part 2)	: 55N/mm ²
Flexural Strength (ISO178)	: 21N/mm ²
Dynamic E-Modulus (ASTM C597-83)	: 14000N/mm ²
Tensile Strength (ISO R527)	: 9N/mm ²
Concrete Adhesion (BS6319:Part2)	: concrete fails
Abrasion Resistance (Taber H22)	: 1410mg
(Taber CS17)	: 120mg
Coeff. Thermal Expansion (ASTM C531)	: 3.6x10 ⁻⁵ °C ⁻¹
Thermal Conductivity (BS874)	: 0.9W/m°C
Surface Resistivity (BS2050)	: 2x10 ¹¹ ohms
Density (BS6319:Part)	: 1970 kg/m ³
Water Adsorption (CP.BM 2/67/2)	: 0 mL
Surface Spread of Flame (BS476:Part 7)	: Class 2

PROPERTIES

Colours	:	Yellow ~ RAL 1004
		Cream ~ RAL 1014
		Orange ~ RAL 2010
		Red ~ RAL 3001
		Green ~ RAL 6010
		Grey ~ RAL 7037
Thickness	:	4 to 6 mm.
Service temperatures:		
at 6 mm	:	60°C maximum & -15°C
at 4 mm	:	60°C maximum & -15°C

APPLICATION

Surface Preparation

Concrete shall be clean, structurally sound and free from foreign materials, contaminants, oily products and other debris. Concrete surfaces shall be 'visibly dry' with no standing water. The minimum tensile (pull-off) strength shall be 1.5N/mm² and concrete shall have cured for at least 5 days. Concrete substrates shall incorporate a continuous waterproofing membrane.

Concrete design shall allow provisions for movement joints, as required. In addition, provision shall be made for induced joints to allow any shrinkage of the concrete to occur along defined planes.

All laitance shall be removed. All imperfections such as holes and cracks shall be repaired and levelled with the mean level of the surface. For repairing surface unevenness, **EMACO[®]** concrete repair systems shall be used.

The whole surface shall be enclosed and impact shot blasted, surface planed, ground or high-pressure water jetted. All high spots shall be removed. Surfaces shall be rendered 'visibly dry' by heat or mechanical means. Remove all loose material and dust by vacuum or other mechanical means.

Priming

Ucrete MF shall be applied to a cured scratch coat of **Ucrete MF** of 1 mm nominal thickness.

Placing

Ucrete MF shall be mixed and applied only by specialist flooring contractors who have been trained in the correct application procedures.

CURING

At 30°C, foot traffic access in 8 hours, vehicular traffic in 16 hours. At 20°C, foot traffic access in 12 hours, vehicular traffic in 24 hours.



The Chemical Company

UCRETE[®] MF

CLEANING

Regular cleaning, dry or wet mechanical scrubbing or hot flushing with detergents or detergent / sterilant products will enhance the floor's appearance and reduce soiling tendencies.

ESTIMATING DATA

2.25 to 2.50 kg/m²/mm thickness

PACKAGING

Ucrete MF is supplied in units for immediate use, consisting of:

Ucrete MF Part 1 : 2.83 kg

Ucrete MF Part 2 : 2.86 kg

Ucrete MF Part 3 : 14.0 kg

SHELF LIFE

Ucrete MF can be kept for 12 months from date of manufacture when stored at 30°C or less above ground level and under cover in original unopened packaging, away from exposure to direct sunlight.

PRECAUTIONS

Material Safety Data Sheets (MSDS) for each component of Ucrete MF are available. Gloves and eye protection shall be worn during mixing and application.

For detailed Health, Safety and Environmental Recommendations, please consult and follow all instructions on the product Material Safety Data Sheet.

OTHER INFORMATION

'Design and Preparation of substrates for Ucrete Flooring'
'BS8204:Part1:1987 – Insitu Flooring – code of practice for concrete bases and screed to receive insitu flooring'
'ICRI-Selection of surface preparation methods for concrete substrates receiving resin flooring'.

BASF Construction Chemicals Product Data Sheets for: EMACO[®] concrete repair products.

All BASF Construction Chemicals Australia & New Zealand data sheets are updated on a regular basis, it is the user's responsibility to obtain the most recent issue **AUcMF/4/0906**

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this **BASF Construction Chemicals** publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by **BASF Construction Chemicals** either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not **BASF Construction Chemicals**, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals Australia Pty Ltd
Incorporated in NSW A.B.N. 46 000 450 288
Head Office: 11 Stanton Road Seven Hills, NSW 2147
Ph. (02) 8811 4200

Newcastle (02) 4961 3819
Canberra (02) 6280 6010
Brisbane (07) 3633 9900
Townsville (07) 4774 7344
Melbourne (03) 9567 7300

Adelaide (08) 8139 7500
Perth (08) 9366 2600
Darwin (08) 8984 3269
Kalgoorlie 0417 772 355

BASF Construction Chemicals New Zealand Ltd Head Office: 45 William Pickering Drive, Albany, Auckland Ph: (09) 414 7233
BASF WEB SITES www.basf-cc.com.au www.basf-cc.co.nz www.basf-uqc.com